



SYMPHONY™

ALUMINUM FOIL LAMINATES

Common Thickness Choices	O₂TR <i>(cc/100in²-day)</i>	WVTR <i>(g/100in²-day)</i>	Foil Appearance before Laminating	Inherent Pinhole Level
0.00030"	0.01	0.01	Bright one side, dull one side	High
0.00035"	0.001	0.002	Bright one side, dull one side	Medium
0.00050"	0.001	0.001	Bright one side, dull one side	Low
0.00075"	0.001	0.001	Bright one side, dull one side	Occasional
0.001"	<0.000	<0.000	Bright one side, dull one side or Bright two sides	None
0.0015"	<0.000	<0.000	Bright two sides	None
0.002"	<0.000	<0.000	Bright two sides	None
0.005"	<0.000	<0.000	Bright two sides	None
0.008"	<0.000	<0.000	Bright two sides	None

02 03/16